

Jiangyou Hacer Technology Co., Ltd.

Steel Grade: P295GH/17Mn4 | Material No: 1.0481

CHEMICAL COMPOSITION

C(%) ≤	Si(%) ≤	Mn(%) ≤	P(%) ≤	S(%) ≤	Cr(%)	Mo(%)	Ni(%)	Other(%)
0.08~0.20	≤0.40	0.90~1.50	0.03	0.025	≤0.30	≤0.08	≤0.30	Cu ≤ 0.30①; Al ≤ 0.020; Nb ≤ 0.01; Ti ≤ 0.03; V ≤ 0.02

HARDNESS AND HEAT TREATMENT MECHANICAL PROPERTIES

Hot Working °C	Annealing/Normalizing °C	Quench °C	Temper °C	Brinell Hardness HBS	Tensile Strength $\sigma_b \geq$ Mpa	Normal Temp Yield Strength $\sigma_s \geq$ Mpa	Extensibility $\delta_5 \geq$ (%)	Ballistic $ak_v \geq$ J⑥		
1100~850	890~950③/520~580④	—	—	130~170	460~580	285	22	47		
Yield Strength $\sigma_{0.2} \geq$ /Mpa					Creep Limit/Mpa 1000h					
200°C	300°C	350°C	400°C	450°C	500°C	450°C	500°C	550°C	600°C	10000h 450°C
225	185	170	155	115	—	—	—	—	—	93
Creep Limit/Mpa 10000h			Creep Rupture/Mpa 1000h			Creep Rupture/Mpa 10000h				
500°C	550°C	600°C	450°C	500°C	550°C	600°C	450°C	500°C	550°C	600°C
—	—	—	59	—	—	—	143	—	—	—

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897 (WhatsApp)
 Fax: +86-(0)816-3260757