

Steel Grade: P275NL1/TStE285 Material No: 1.0488														
CHEMICAL COMPOSITION														
C(%) ≤	Si (%)	Mn (%)≤	P (%)≤	S (%)≤	N (%)≤	Al (%)	Cr (%)≤	Cu (%)≤	Mo (%)≤	Ni (%)≤	Nb (%)≤	Ti (%)≤	V (%)	Nb+Ti +V(%)⑥
0.16	≤0.40	0.50~1.50	0.03	0.02	0.02	0.02	0.30②	0.30②	0.08②	0.5	0.05	0.03	0.05	0.05
MECHANICAL PROPERTIES														
Tensile Strength σ_b /Mpa					Normal Temp Yield Strength σ /Mpa									
≤70mm	70-85mm	85-100mm	100-125mm	125-150mm	≤16mm	16-35mm	35-50mm	50-60mm	60-70mm	70-85mm	85-100mm	100-125mm	125-150mm	
390~510	380~500	370~490	360~480	350~470	285	285	275	265	265	255	245	235	225	
Extensibility $\delta_5 \geq$ (%)	Flexural Center Dia Cold-bend Test		Sample Direction L/T⑧⑨	Ballistic $ak_v \geq$ (J/cm ²)										
	180°C/L	180°C/T ⑥⑦		+20°C	+10°C	+0°C	-10°C	-20°C	-30°C	-40°C	-50°C	-60°C		
24	1.5a	2a	L/T	63/39	59/35	55/31	51/31	47/27	39/24	31/20	27/16	—/—		

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897 (WhatsApp)
 Fax: +86-(0)816-3260757