

Steel Grade: S355N   Material No: 1.0545														
CHEMICAL COMPOSITION														
C(%) ≤	Si (%)	Mn (%)≤	P (%)≤	S (%)≤	N (%)≤	Al (%)	Cr (%)≤	Cu (%)≤	Mo (%)≤	Ni (%)≤	Nb (%)≤	Ti (%)≤	V (%)	Nb+Ti +V(%)⑥
0.2	≤0.50	0.90~1.65	0.035	0.03	0.015	0.02	0.30②	0.35	0.1	0.50④	0.05	0.03	0.12	—
MECHANICAL PROPERTIES														
Tensile Strength   $\sigma_b$ /Mpa					Normal Temp Yield Strength   $\sigma$ /Mpa									
≤70mm	70-85mm	85-100mm	100-125mm	125-150mm	≤16mm	16-35mm	35-50mm	50-60mm	60-70mm	70-85mm	85-100mm	100-125mm	125-150mm	
—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Extensibility   $\delta_5 \geq$ (%)	Flexural Center Dia Cold-bend Test		Sample Direction L/T⑧⑨	Ballistic   $ak_v \geq$ (J/cm <sup>2</sup> )										
	180°C/L	180°C/T ⑥⑦		+20°C	+10°C	+0°C	-10°C	-20°C	-30°C	-40°C	-50°C	-60°C		
	—	—		L/T	—/—	—/—	—/—	—/—	—/—	—/—	—/—	—/—	—/—	—/—

From: Jiangyou Hacer Technology Co., Limited  
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China  
 Website: <https://www.jhacer.com/>  
 Email: sales@jhacer.com  
 Phone: +86-(0)816-3260757  
 Call: +86-13658128897(WhatsApp)  
 Fax: +86-(0)816-3260757