

Steel Grade: P355NH/WStE355 Material No: 1.0565														
CHEMICAL COMPOSITION														
C(%) ≤	Si (%)	Mn (%)≤	P (%)≤	S (%)≤	N (%)≤	Al (%)	Cr (%)≤	Cu (%)≤	Mo (%)≤	Ni (%)≤	Nb (%)≤	Ti (%)≤	V (%)	Nb+Ti +V(%)⑥
0.2	≤0.50	0.90~1.70	0.03	0.025	0.02	0.02	0.30②	0.30②	0.08②	0.50④	0.05	0.03	0.1	0.12
MECHANICAL PROPERTIES														
Tensile Strength σ_b /Mpa					Normal Temp Yield Strength σ /Mpa									
≤70mm	70-85mm	85-100mm	100-125mm	125-150mm	≤16mm	16-35mm	35-50mm	50-60mm	60-70mm	70-85mm	85-100mm	100-125mm	125-150mm	
490~630	480~620	470~600	460~600	450~590	355	355	345	325	325	315	315	295	295	
Extensibility $\delta_5 \geq$ (%)	Flexural Center Dia Cold-bend Test		Sample Direction L/T⑧⑨	Ballistic $ak_v \geq$ (J/cm ²)										
	180°C/L	180°C/T ⑥⑦		+20°C	+10°C	+0°C	-10°C	-20°C	-30°C	-40°C	-50°C	-60°C		
22	2a	3a	L/T	55/31	51/31	47/31	43/24	39/21	—/—	—/—	—/—	—/—	—/—	—/—
Steel Size/mm	High Temp Yield Strength $\sigma_{0.2} \geq$ Mpa													
	100°C	150°C	200°C	250°C	300°C	350°C	400°C							
	≤35	304	284	—	—	—	—	—	—	—	—	—	—	—
	100~125	265	245	226	206	186	167	137						
125~150	255	235	216	196	177	127								

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897(WhatsApp)
 Fax: +86-(0)816-3260757