

Steel Grade: 21CrMoV5-7 | Material No: 1.7709

CHEMICAL COMPOSITION

C(%) ≤	Si(%) ≤	Mn(%) ≤	P(%) ≤	S(%) ≤	Cr(%)	Mo(%)	Ni(%)	Other(%)
0.17~0.25	0.15~0.35	0.35~0.85	0.03	0.035	1.20~1.50	0.65~0.80	—	V 0.25~0.35

HARDNESS AND HEAT TREATMENT MECHANICAL PROPERTIES

Hot Working °C	Annealing/Normalizing °C	Quench °C	Temper °C	Brinell Hardness HBS	Tensile Strength $\sigma_b \geq$ Mpa	Normal Temp Yield Strength $\sigma_s \geq$ Mpa	Extensibility $\delta_5 \geq$ (%)	Ballistic $ak_v \geq$ J⑥		
1100~850	650~730	890~940 Oil	680~720	205~250	700~850	550	16	69		
Yield Strength $\sigma_{0.2} \geq$ /Mpa					Creep Limit/Mpa 1000h					
200°C	300°C	350°C	400°C	450°C	500°C	450°C	500°C	550°C	600°C	10000h 450°C
500	460	441	412	372	334	—	—	—	—	361
Creep Limit/Mpa 10000h			Creep Rupture/Mpa 1000h				Creep Rupture/Mpa 10000h			
500°C	550°C	600°C	450°C	500°C	550°C	600°C	450°C	500°C	550°C	600°C
242	138	—	288	175	74	—	405	271	170	—

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897 (WhatsApp)
 Fax: +86-(0)816-3260757