

Steel Grade: 24CrMoV5-5 | Material No: 1.7733

CHEMICAL COMPOSITION

C(%) ≤	Si(%) ≤	Mn(%) ≤	P(%) ≤	S(%) ≤	Cr(%)	Mo(%)	Ni(%)	Other(%)
0.20~0.28	0.15~0.35	0.30~0.60	0.035	0.025	1.20~1.50	0.50~0.60	≤0.60	V 0.15~0.25

HARDNESS AND HEAT TREATMENT MECHANICAL PROPERTIES

Hot Working °C	Annealing/Normalizing °C	Quench °C	Temper °C	Brinell Hardness HBS	Tensile Strength $\sigma_b \geq$ Mpa	Normal Temp Yield Strength $\sigma_s \geq$ Mpa	Extensibility $\delta_5 \geq$ (%)	Ballistic $ak_v \geq$ J⑥		
1100~850	650~740	900~950 Oil	680~740	205~250	690~830	540	17	55		
Yield Strength $\sigma_{0.2} \geq$ /Mpa					Creep Limit/Mpa 1000h					
200°C	300°C	350°C	400°C	450°C	500°C	450°C	500°C	550°C	600°C	10000h 450°C
490	451	—	402	—	343	412	265	137	—	324
Creep Limit/Mpa 10000h			Creep Rupture/Mpa 1000h				Creep Rupture/Mpa 10000h			
500°C	550°C	600°C	450°C	500°C	550°C	600°C	450°C	500°C	550°C	600°C
206	98	—	265	137	54	—	412	284	167	—

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897 (WhatsApp)
 Fax: +86-(0)816-3260757