

Jiangyou Hacer Technology Co., Ltd.

Steel Grade: 21CrMoV5-11 | Material No: 1.8070

CHEMICAL COMPOSITION

C(%) ≤	Si(%) ≤	Mn(%) ≤	P(%) ≤	S(%) ≤	Cr(%)	Mo(%)	Ni(%)	Other(%)
0.17~0.25	0.30~0.60	0.30~0.60	0.035	0.035	1.20~1.50	1.00~1.20	≤0.60	V 0.25~0.35

HARDNESS AND HEAT TREATMENT MECHANICAL PROPERTIES

Hot Working °C	Annealing/Normalizing °C	Quench °C	Temper °C	Brinell Hardness HBS	Tensile Strength $\sigma_b \geq$ Mpa	Normal Temp Yield Strength $\sigma_s \geq$ Mpa	Extensibility $\delta_5 \geq$ (%)	Ballistic $ak_v \geq$ J⑥		
1100~850	650~740	900~950 Oil	680~720	205~250	700~850	550	16	55		
Yield Strength $\sigma_{0.2} \geq$ /Mpa					Creep Limit/Mpa 1000h					
200°C	300°C	350°C	400°C	450°C	500°C	450°C	500°C	550°C	600°C	10000h 450°C
510	481	461	431	402	373	441	294	157	—	353
Creep Limit/Mpa 10000h			Creep Rupture/Mpa 1000h			Creep Rupture/Mpa 10000h				
500°C	550°C	600°C	450°C	500°C	550°C	600°C	450°C	500°C	550°C	600°C
235	118	—	275	167	64	—	441	304	177	—

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897 (WhatsApp)
 Fax: +86-(0)816-3260757