

Steel Grade: TStE500(S500NL)   Material No: 1.8917														
CHEMICAL COMPOSITION														
C(%) ≤	Si (%)	Mn (%)≤	P (%)≤	S (%)≤	N (%)≤	Al (%)	Cr (%)≤	Cu (%)≤	Mo (%)≤	Ni (%)≤	Nb (%)≤	Ti (%)≤	V (%)	Nb+Ti +V(%)⑥
0.21	0.10~0.60	1.00~1.70	0.03	0.025	0.02	0.02	0.3	0.7	0.1	1	0.05	—⑤	0.22	0.22
MECHANICAL PROPERTIES														
Tensile Strength   $\sigma_b$ /Mpa					Normal Temp Yield Strength   $\sigma$ /Mpa									
≤70mm	70-85mm	85-100mm	100-125mm	125-150mm	≤16mm	16-35mm	35-50mm	50-60mm	60-70mm	70-85mm	85-100mm	100-125mm	125-150mm	
610~780	600~770	590~760	580~750	570~740	500	480	470	460	450	440	430	420	410	
Extensibility   $\delta_5 \geq$ (%)	Flexural Center Dia Cold-bend Test		Sample Direction L/T⑧⑨	Ballistic   $ak_v \geq$ (J/cm <sup>2</sup> )										
	180°C/L	180°C/T ⑥⑦		+20°C	+10°C	+0°C	-10°C	-20°C	-30°C	-40°C	-50°C	-60°C		
16	3a	4a	L/T	63/39	59/35	55/31	51/31	47/27	39/24	31/20	27/16	—/—		

From: Jiangyou Hacer Technology Co., Limited  
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China  
 Website: <https://www.jhacer.com/>  
 Email: [sales@jhacer.com](mailto:sales@jhacer.com)  
 Phone: +86-(0)816-3260757  
 Call: +86-13658128897 (WhatsApp)  
 Fax: +86-(0)816-3260757