

Steel Grade: WStE380(P380NH)   Material No: 1.8930														
CHEMICAL COMPOSITION														
C(%) ≤	Si (%)	Mn (%)≤	P (%)≤	S (%)≤	N (%)≤	Al (%)	Cr (%)≤	Cu (%)≤	Mo (%)≤	Ni (%)≤	Nb (%)≤	Ti (%)≤	V (%)	Nb+Ti +V(%) <sup>⑥</sup>
0.2	0.10~0.60	1.00~1.70	0.035	0.03	0.02	0.02	0.3	0.2	0.08 <sup>②</sup>	1	0.05	— <sup>⑤</sup>	0.2	0.22
MECHANICAL PROPERTIES														
Tensile Strength   $\sigma_b$ /Mpa					Normal Temp Yield Strength   $\sigma$ /Mpa									
≤70mm	70-85mm	85-100mm	100-125mm	125-150mm	≤16mm	16-35mm	35-50mm	50-60mm	60-70mm	70-85mm	85-100mm	100-125mm	125-150mm	
500~650	490~640	480~630	470~620	460~610	380	375	365	355	345	335	325	315	305	
Extensibility   $\delta_5 \geq$ (%)	Flexural Center Dia Cold-bend Test		Sample Direction L/T <sup>⑧⑨</sup>	Ballistic   $ak_v \geq$ (J/cm <sup>2</sup> )										
	180°C/L	180°C/T ⑥⑦		+20°C	+10°C	+0°C	-10°C	-20°C	-30°C	-40°C	-50°C	-60°C		
20	2.5a	3.5a	L/T	55/31	51/31	47/31	43/24	39/21	—/—	—/—	—/—	—/—	—/—	—/—
Steel Size/mm	High Temp Yield Strength   $\sigma_{0.2} \geq$ Mpa													
	100°C	150°C	200°C	250°C	300°C	350°C	400°C							
	≤35	333	314	—	—	—	—	—	—	—	—	—	—	—
	100~125	294	275	255	235	216	186	157						
125~150	284	265	245	226	206	177	147							

From: Jiangyou Hacer Technology Co., Limited  
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China  
 Website: <https://www.jhacer.com/>  
 Email: sales@jhacer.com  
 Phone: +86-(0)816-3260757  
 Call: +86-13658128897 (WhatsApp)  
 Fax: +86-(0)816-3260757