

Steel Grade: C25E/Ck25 Material No: 1.1158								
CHEMICAL COMPOSITION								
C(%)	Si(%)	Mn(%)	P(%)	S(%)	Cr(%)	Mo(%)	Ni(%)	Other(%)
0.22~0.29	≤0.40	0.40~0.70	0.035	0.035	≤0.40	≤0.10	≤0.40	Cr+Mo+Ni < 0.63%
HARDNESS AND HEAT TREATMENT								
Hot Working/°C	Annealing/°C	Normalizing/°C	Quench/°C	Temper/°C	Annealing hardness HBS ≤			
1100~850	650~700	880~910	860~890 Water	540~680	156			
MECHANICAL PROPERTIES								
Size/mm	Tensile Strength σ_b /Mpa	Yield Strength $\sigma_s \geq$ /Mpa	Extensibility δ_5 (%) \geq	Reduction of Area ψ (%) \geq	Ballistic akv/J ^③			
≤16	550~700	370	19	45	50			
17~40	500~650	320	21	50	50			

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897(WhatsApp)