



Jiangyou Hacer Technology Co., Ltd.

Steel Grade: 17CrNiMo6-4 | Material No: 1.6566

CHEMICAL COMPOSITION

C(%)	Si(%)	Mn(%)	P(%) ≤	S(%) ≤	Cr(%)	Mo(%)	Ni(%)	Other(%)
0.14~0.20	≤0.40	0.60~0.90	0.035	0.035	0.80~1.10	0.15~0.25	1.20~1.50	—

HARDNESS AND HEAT TREATMENT

Hot Working/°C	Annealing/°C	Carburize/°C	Inside Quench/°C	Surface Quench/°C	Temper/°C	Annealing hardness HBS ≤
1150~850	650~700	900~950	840~870	800~830 Oil	170~210	229

INSIDE MECHANICAL PROPERTIES

Size/mm	Tensile Strength σ_b /MPa	Yield Strength $\sigma_s \geq$ /MPa	Extensibility $\delta_5(\%) \geq$	Reduction of Area $\psi(\%) \geq$	Ballistic akv/J
φ11	1180~1420	830	7	30	41

From: Jiangyou Hacer Technology Co., Limited
Factory Add: Jiangzhang Road, Jiangyou City, SC, China
Website: <https://www.jhacer.com/>
Email: sales@jhacer.com
Phone: +86-(0)816-3260757
Call: +86-13658128897(WhatsApp)
Fax: +86-(0)816-3260757