

Steel Grade: AISI H41 UNS T20841							
CHEMICAL COMPOSITION							
C(%)	Si(%)	Mn(%)	Cr(%)	Mo(%)	V(%)	W(%)	Other(%)
0.60~0.75	0.20~0.45	0.20~0.40	3.50~4.00	8.20~9.20	1.00~1.30	1.40~2.10	—
HARDNESS AND HEAT TREATMENT							
Initial Forging Temperature/°C	Finish Forging Temperature/°C	Annealing/°C	Hardbess HBS After Annealing	Quenching/°C	Quenching Medium	Tempering/°C	Hardbess HBC After Tempering
1040~1120	930	820~870	207~235	1090~1190	aline、 Oil or A	570~650	60~50

Remark:

- ①, The temperature is after carburization.
- ②, It is surface hardness after carburization.
- ③, Aging treatment.

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897(WhatsApp)