

Steel Grade: AISI P2   UNS T51602							
CHEMICAL COMPOSITION							
C(%)	Si(%)	Mn(%)	Cr(%)	Mo(%)	V(%)	W(%)	Other(%)
0.07	0.20~0.40	0.20~0.40	2	0.2	—	—	Ni0.5
HARDNESS AND HEAT TREATMENT							
Initial Forging Temperature/°C	Finish Forging Temperature/°C	Annealing/°C	Hardbess HBS   After Annealing	Quenching/°C	Quenching Medium	Tempering/°C	Hardbess HBC   After Tempering
1010~1120	840	730~820	103~123	830~840①	Oil	150~260	64~58②

Remark:

- ①, The temperature is after carburization.
- ②, It is surface hardness after carburization.
- ③, Aging treatment.

From: Jiangyou Hacer Technology Co., Limited  
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China  
 Website: <https://www.jhacer.com/>  
 Email: sales@jhacer.com  
 Phone: +86-(0)816-3260757  
 Call: +86-13658128897(WhatsApp)