

Steel Grade: AISI S5 UNS T41905							
CHEMICAL COMPOSITION							
C(%)	Si(%)	Mn(%)	Cr(%)	Mo(%)	V(%)	W(%)	Other(%)
0.50~0.60	1.20~2.20	0.60~0.90	0.3	0.30~0.50	0.25	—	—
HARDNESS AND HEAT TREATMENT							
Initial Forging Temperature/°C	Finish Forging Temperature/°C	Annealing/°C	Hardbess HBS After Annealing	Quenching/°C	Quenching Medium	Tempering/°C	Hardbess HBC After Tempering
1010~1120	870	760~790	192~229	870~930	Oil	180~430	60~50

Remark:

- ①, The temperature is after carburization.
- ②, It is surface hardness after carburization.
- ③, Aging treatment.

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897(WhatsApp)