

| Steel Grade: ASTM 51B60④ | | | | | | | |
|--------------------------|-----------|-----------|-------|-------|-----------|-------|-------|
| CHEMICAL COMPOSITION | | | | | | | |
| C(%) | Si(%)③ | Mn(%) | P(%)≤ | S(%)≤ | Cr(%) | Mo(%) | Ni(%) |
| 0.56~0.64 | 0.15~0.35 | 0.75~1.00 | 0.04 | 0.04 | 0.70~0.90 | — | — |

Remark:

- ①, Remnant element:Cr≤0.20%, Mo≤0.06%, Ni≤0.25%, Cu≤0.35%
- ②, When the ω(Pb) is between 0.15% and 0.35%, the steel grade should be added "L" between the second number and the third number.
- ③, We can supply the steel of ω(Si)≤0.15%, if you want to use it to cold forming parts, please choose ω(Si)≤0.10%.
- ④, It is boron steel and the ω(B) is 0.0005%~0.003%, can not contain Ti, the max ω(B) is 0.005%.

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, Chi
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call:+86-13658128897(WhatsApp)
 Fax: +86-(0)816-3260757