



## Jiangyou Hacer Technology Co., Ltd.

Steel Grade: ASTM A709 Gr.50type 4 | 0.0000

### CHEMICAL COMPOSITION

C (%)	Si (%)	Mn (%)	P (%)	S (%)	Cu (%)	V (%)	Other (%)
0.23	0.40	1.35	0.04	0.05	—	—	Nb ≤ 0.015

### MECHANICAL PROPERTIES

Thickness/mm	Tensile Strength   $\sigma_b$ /MPa	Yield Strength   $\sigma_s \geq$ /MPa	Extensibility   $\delta$ ③ (%)	Cold-bend Test(180°C/L)①	Cold-bend Test(180°C/T) ①
100	450	21	—	345	—
100	485	21	—	345	—

Remark:

- ①, The d which is flexural Center Dia is integral multiple as a which is thickness of steel.
- ②, We can meet any additional conditions within ASTM6 standard.
- ③, The distance of testing sample is 50mm.

From: Jiangyou Hacer Technology Co., Limited  
Factory Add: Jiangzhang Road, Jiangyou City, SC,  
Website: <https://www.jhacer.com/>  
Email: [sales@jhacer.com](mailto:sales@jhacer.com)  
Phone: +86-(0)816-3260757  
Call: +86-13658128897(WhatsApp)  
Fax: +86-(0)816-3260757