

Steel Grade: ASTM M1031			
CHEMICAL COMPOSITION			
C(%)	Mn(%)	P(%) ≤	S(%) ≤
0.26~0.36	0.25~0.60	0.04	0.05

Remark:

- 1, If you don't mind, the Mn component will be exceeded 0.60% to reach 0.75%, then each the Mn component added 0.05%, the C component will be reduced
- 2, The standard is ASTM A29/29M(1999) and SAE J403(1995).

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897(WhatsApp)
 Fax: +86-(0)816-3260757