

Steel Grade: ASTM M36 | UNS T11336 | Type: Molybdenum Series

**CHEMICAL COMPOSITION**

C(%)	Si(%)	Mn(%)	P(%) ≤	S(%) ≤②	Cr(%)	Mo(%)	V(%)	W(%)	Co(%)
0.80~0.90	0.20~0.45	0.15~0.40	0.03	0.03	3.75~4.50	4.50~5.50	1.75~2.25	5.50~6.50	7.75~8.75

**HARDNESS AND HEAT TREATMENT**

Hardness HBS			Preheating Temperature/ °C	Quenching/°C		Tempering/°C	Hardness ≥ HRC   After Tempering
Annealing	Cold Drawing	Annealing after Cold Drawing		Salt-Bath Furnace	Controlled Atmosphere Furnace		
269	285	277	732~843	1204	1216	552	64

Remark:

①,  $\omega(\text{Cu} + \text{Ni}) \leq 0.75\%$

②, The composition of S can be increased to  $\omega(\text{S}) 0.06\% \sim 0.15\%$  in order to improve the performance of

③, The standard is ASTM A600-1999.

From: Jiangyou Hacer Technology Co., Limited  
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China  
 Website: <https://www.jhacer.com/>  
 Email: [sales@jhacer.com](mailto:sales@jhacer.com)  
 Phone: +86-(0)816-3260757  
 Call: +86-13658128897(WhatsApp)