

Steel Grade: ASTM M47 | UNS T11347 | Type: Molybdenum Series

**CHEMICAL COMPOSITION**

C(%)	Si(%)	Mn(%)	P(%) ≤	S(%) ≤②	Cr(%)	Mo(%)	V(%)	W(%)	Co(%)
1.05~1.15	0.20~0.45	0.15~0.40	0.03	0.03	3.50~4.00	9.25~10.0	1.15~1.35	1.30~1.80	4.75~5.25

**HARDNESS AND HEAT TREATMENT**

Hardness HBS			Preheating Temperature/ °C	Quenching/°C		Tempering/°C	Hardness ≥ HRC   After Tempering
Annealing	Cold Drawing	Annealing after Cold Drawing		Salt-Bath Furnace	Controlled Atmosphere Furnace		
269	285	277	732~843	1190	1202	538	66

Remark:

①,  $\omega(\text{Cu} + \text{Ni}) \leq 0.75\%$

②, The composition of S can be increased to  $\omega(\text{S}) 0.06\% \sim 0.15\%$  in order to improve the performance of

③, The standard is ASTM A600-1999.

From: Jiangyou Hacer Technology Co., Limited  
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China  
 Website: <https://www.jhacer.com/>  
 Email: [sales@jhacer.com](mailto:sales@jhacer.com)  
 Phone: +86-(0)816-3260757  
 Call: +86-13658128897(WhatsApp)