



# Jiangyou Hacer Technology Co., Ltd.

Steel Grade: ASTM T5 | UNS T12005 | Type: Tungsten Series

## CHEMICAL COMPOSITION

C(%)	Si(%)	Mn(%)	P(%) ≤	S(%) ≤②	Cr(%)	Mo(%)	V(%)	W(%)	Co(%)
0.75~0.85	0.20~0.40	0.20~0.40	0.03	0.03	3.75~5.00	0.50~1.25	1.80~2.40	17.5~19.0	7.00~9.50

## HARDNESS AND HEAT TREATMENT

Hardness HBS			Preheating Temperature/ °C	Quenching/°C		Tempering/°C	Hardness ≥ HRC   After Tempering
Annealing	Cold Drawing	Annealing after Cold Drawing		Salt-Bath Furnace	Controlled Atmosphere Furnace		
285	302	293	816~871	1277	1288	552	63

Remark:

①,  $\omega(\text{Cu} + \text{Ni}) \leq 0.75\%$

②, The composition of S can be increased to  $\omega(\text{S}) 0.06\% \sim 0.15\%$  in order to improve the performance of

③, The standard is ASTM A600-1999.

From: Jiangyou Hacer Technology Co., Limited  
Factory Add: Jiangzhang Road, Jiangyou City, SC, China  
Website: <https://www.jhacer.com/>  
Email: [sales@jhacer.com](mailto:sales@jhacer.com)  
Phone: +86-(0)816-3260757  
Call: +86-13658128897(WhatsApp)