



Jiangyou Hacer Technology Co., Ltd.

Steel Grade: ASTM T8 | UNS T12008 | Type: Tungsten Series

CHEMICAL COMPOSITION

| C(%) | Si(%) | Mn(%) | P(%) ≤ | S(%) ≤② | Cr(%) | Mo(%) | V(%) | W(%) | Co(%) |
|-----------|-----------|-----------|--------|---------|-----------|-----------|-----------|-------------|-----------|
| 0.75~0.85 | 0.20~0.40 | 0.20~0.40 | 0.03 | 0.03 | 3.75~4.50 | 0.40~1.00 | 1.80~2.40 | 13.25~14.75 | 4.25~5.75 |

HARDNESS AND HEAT TREATMENT

| Hardness HBS | | | Preheating Temperature/ °C | Quenching/°C | | Tempering/°C | Hardness ≥ HRC After Tempering |
|--------------|-----------------|---------------------------------|-------------------------------|----------------------|-------------------------------------|--------------|-------------------------------------|
| Annealing | Cold Drawing | Annealing after Cold Drawing | | Salt-Bath Furnace | Controlled Atmosphere Furnace | | |
| 255 | 269 | 262 | 816~871 | 1277 | 1288 | 552 | 63 |

Remark:

①, $\omega(\text{Cu} + \text{Ni}) \leq 0.75\%$

②, The composition of S can be increased to $\omega(\text{S}) 0.06\% \sim 0.15\%$ in order to improve the performance of

③, The standard is ASTM A600-1999.

From: Jiangyou Hacer Technology Co., Limited
Factory Add: Jiangzhang Road, Jiangyou City, SC, China
Website: <https://www.jhacer.com/>
Email: sales@jhacer.com
Phone: +86-(0)816-3260757
Call: +86-13658128897(WhatsApp)