

Steel Grade: ASTM M10(Normal C%) | UNS T11310 | Type: Molybdenum Series

CHEMICAL COMPOSITION

C(%)	Si(%)	Mn(%)	P(%) ≤	S(%) ≤②	Cr(%)	Mo(%)	V(%)	W(%)	Co(%)
0.84~0.94	0.20~0.45	0.10~0.40	0.03	0.03	3.75~4.50	7.75~8.50	1.80~2.20	—	—

HARDNESS AND HEAT TREATMENT

Hardness HBS			Preheating Temperature/ °C	Quenching/°C		Tempering/°C	Hardness ≥ HRC After Tempering
Annealing	Cold Drawing	Annealing after Cold Drawing		Salt-Bath Furnace	Controlled Atmosphere Furnace		
248	262	255	732~843	1196	1207	552	63

Remark:

①, $\omega(\text{Cu} + \text{Ni}) \leq 0.75\%$

②, The composition of S can be increased to $\omega(\text{S}) 0.06\% \sim 0.15\%$ in order to improve the performance of

③, The standard is ASTM A600-1999.

From: Jiangyou Hacer Technology Co., Limited
 Factory Add: Jiangzhang Road, Jiangyou City, SC, China
 Website: <https://www.jhacer.com/>
 Email: sales@jhacer.com
 Phone: +86-(0)816-3260757
 Call: +86-13658128897(WhatsApp)