



Jiangyou Hacer Technology Co., Ltd.

Steel Grade: ASTM T6 | UNS T12006 | Type: Tungsten Series

CHEMICAL COMPOSITION

C(%)	Si(%)	Mn(%)	P(%) ≤	S(%) ≤②	Cr(%)	Mo(%)	V(%)	W(%)	Co(%)
0.75~0.85	0.20~0.40	0.20~0.40	0.03	0.03	4.00~4.75	0.40~1.00	1.50~2.10	18.5~21.0	11.0~13.0

HARDNESS AND HEAT TREATMENT

Hardness HBS			Preheating Temperature/ °C	Quenching/°C		Tempering/°C	Hardness ≥ HRC After Tempering
Annealing	Cold Drawing	Annealing after Cold Drawing		Salt-Bath Furnace	Controlled Atmosphere Furnace		
302	321	311	816~871	1277	1288	552	63

Remark:

①, $\omega(\text{Cu} + \text{Ni}) \leq 0.75\%$

②, The composition of S can be increased to $\omega(\text{S}) 0.06\% \sim 0.15\%$ in order to improve the performance of

③, The standard is ASTM A600-1999.

From: Jiangyou Hacer Technology Co., Limited
Factory Add: Jiangzhang Road, Jiangyou City, SC, China
Website: <https://www.jhacer.com/>
Email: sales@jhacer.com
Phone: +86-(0)816-3260757
Call: +86-13658128897(WhatsApp)